















POLYMO COLOR











顔料

POLYMOカラーは、高品質な顔料を高濃度で均一に分散させた水分散性カラーです。

被染物 綿サテン

染色法 捺染法

染料名	色見本	耐光(20h)		洗濯 (A-4)	ドライクリーニング (Exxsol D40)	耐ロンガ リット性 (Rongalite)	耐塩化錫 (SnCl ₂)	耐熱性 (200℃)
		濃色	淡色					
1 Yellow FF3G		7-8	6-7	5	4	5	5	4-5
2 Yellow FG-EX		7	5	5	4	5	5	4
3 Yellow FF2R CONC		7-8	7-8	5	4	5	5	4-5
4 Orange GR		6	4	5	4	5	5	3-4
5 Red FFG-N		5-6	5	5	4	3-4	3	3-4
6 Red FFTGK-2		8	7	5	5	5	5	4-5
7 Red FTR		6-7	5	5	4	3-4	3	3-4
8 Red FB		7-8	5-6	5	4	4	4	4
9 Red R NEW		6	5	5	4	2	2	4
10 Red FFB		6	5	5	4	4	4	4
11 Rose FBL		7	4-5	5	4	3	3	3-4
12 Brown FG		5-6	3-4	5	4	2-3	2-3	3
13 Brown GR-A		5-6	3-4	5	4	2	2	3
14 Brown FR		5-6	3-4	5	4	2	2	3

15	Violet FWT		8	7-8	5	4	5	5	4-5
16	Blue FFG		7-8	6-7	5	4	5	5	4
17	Blue R		7-8	6-7	5	4	4-5	5	4
18	Navy Blue R		8	7-8	5	4-5	5	5	4
19	Navy Blue B		8	7-8	5	4-5	5	5	4
20	Sky Blue FF2GR		8	7-8	5	4	5	5	4-5
21	Sky Blue H		8	7-8	5	4	5	5	4
22	Green FBH		8	7-8	5	4	4	5	4
23	Grey G		8	7-8	5	4-5	5	5	5
24	Black FB		8	8	5	5	5	5	5

試験方法

耐光(20h) : JIS L 0842-1996 カーボンアーク 20h

洗濯(A-4) : JIS L 0844-1997 A-4法

ドライクリーニング : JIS L 0860-1996 EXXSOL D40使用

耐還元性 : ロンガリットC 10%添加の着抜試験

耐錫性 : 塩化第一錫8%添加の着抜試験

耐熱性(200℃) : 200℃×30秒

注記 : お客様の環境によっては、正確に表示及び印刷できない項目や色等ある場合がございますが、ご了承下さい。