









VAT DYES

VAT DYESTUFF SERIES

Dyeable by exhaustion and continuous dyeing with the excellent ability of light, solvent and chlorine-resistance fastness.

Dyeable in changing chemical structure by the reaction of oxidation-reduction and utilizing the characteristics of dissolution / insolubilization in the water.

Name of dyestuff	Color sample	Light Fastness (Carbon 20h)	Washing (A-4)		Chlorinated water 2 0 p p m
			Cotton	Silk	
1 Yellow K3G		7	5	4-5	4-5
2 Red FBB		6-7	5	4-5	4
3 Violet KBN		6-7	5	4-5	4
4 Blue K-CL		6-7	5	4-5	4
5 Blue BC		7	5	4-5	3-4
6 Brown BR		7	5	4-5	4
7 Olive T		7-8	5	4-5	4
8 Grey KB		7	4-5	4	3-4

Test Method

Light Fastness : JIS L 0842-1996 Carbon Arc 20h
(Carbon 20h)

Washing (A-4) : JIS L 0844-1997 A-4 method

Chlorinated water (20ppm) : JIS L 0884-1996 Effective chlorine 20ppm

Notice: Please note that depending on your environment, there are some items and colors that can not be accurately displayed nor printed.